

Montego

Artificial leather collection

Technical data sheet

GENERAL		
Composition surface		100%PVC
Composition back cloth		100%PL
Roll width		>137cm
Roll length		30m
Weight (UNI EN ISO 12127)		650gr/m ²
Thickness		1.20mm
TESTS	METHOD	RESULT / U.M.
Fastness to rubbing (dry/wet)	UNI EN ISO 11640	dry 5 / wet >=4-5
Colour fastness to light	UNI EN ISO 105 B02	>6
Colour fastness to perspiration (acid/alkali)	UNI EN ISO 11641	5
Flexing endurance Bally Flex	UNI EN ISO 4818/92	>100.000
Resistance to blocking	UNI EN ISO BS 3424	no blocking
Martindale abrasion	UNI EN ISO 12947-2	>60.000
Anti-bacterial activity	UNI EN ISO 20743-8.2	pass
Burning behaviour	UNI EN ISO 1021 part 1+2 FR BS 5852 source 0+1	pass

GENERAL INFORMATION



Fireproof



Easy to clean



UV and low formaldehyde resistant



Long life



REACH compliant



Waterproof



Antibacterial



Abrasion resistant



Easy to clean

CLEANING INSTRUCTIONS

Wipe clean with a slightly wet cloth. Use water and neutral soap. Use stain remover suited for artificial leather. Following disinfectants do not have a negative impact on the coating: sagrotan med, octenisept, isopropylalcohol, dettol (10% solution), sterilium, softasept, jood tinktur, kodan tinktur forte, hansasmed spray, sagrotan spray.

REMARKS

INTENSIVE DOMESTIC AND CONTRACT USE

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the artificial leather.