


Rendena

Genuine leather collection

Technical data sheet

GENERAL		
Thickness		1,2-1,4mm
Average surface		4,8-5,0sqm
Finishing		half-grain S.A. bovine
TESTS	METHOD	RESULT / U.M.
Fastness to rubbing Veslic - dry	UNI EN ISO 11640	>= 4
Fastness to rubbing Veslic - wet	UNI EN ISO 11640	>= 3/4
Colour fastness to light	UNI EN ISO 105 B02	>= 5
Sweat fastness (alkaline solution)	UNI EN ISO 11640	>= 3/4
Flexing endurance Bally Flex	UNI EN ISO 5402	>50.000 cycles
Tear strength (Bauman method)	UNI EN 3377-1	>= 20 N
Finish adhesion	UNI EN ISO 11644	>= 2,5 N/cm
Burning behaviour	IMO RES A652 (16) - MED B336	pass
CERTIFICATS		
 FIRE RETARDANT		
CLEANING INSTRUCTIONS		
Slightly damp cloth		
REMARKS		
INTENSIVE USE FOR CONTRACT, DOMESTIC AND INDUSTRY Slight color differences between production batches can occur. The test results only apply to the samples tested. Buvetex can't be kept liable for inappropriate use of the genuine leather.		