

Burlina

Genuine leather collection

Technical data sheet

GENERAL		
Thickness		1,2-1,4mm
Average surface		4,8-5,0sqm
Finishing		half grain Eur. bovine
Tanning		chrome tanned
TESTS	METHOD	RESULT / U.M.
Fastness to rubbing Veslic - dry	UNI EN ISO 11640	>= 4
Fastness to rubbing Veslic - wet	UNI EN ISO 11640	>= 3-4
Colour fastness to light	UNI EN ISO 105 B02	>= 5
Sweat fastness (alkaline solution)	UNI EN ISO 11640	>= 3-4
Flexing endurance Bally Flex	UNI EN ISO 5402	>50.000 cycles
Tear strength (Bauman method)	UNI EN 3377-1	>= 20 N
Finish adhesion	UNI EN ISO 11644	>= 2 N/cm
CERTIFICATS		
CLEANING INSTRUCTIONS		
Slightly damp cloth		
REMARKS		
<p>***INTENSIVE USE FOR CONTRACT, DOMESTIC AND INDUSTRY***</p> <p>Slight color differences between production batches can occur.</p> <p>The test results only apply to the samples tested.</p> <p>Buvetex can't be kept liable for inappropriate use of the genuine leather.</p>		