

# Collection Billie

Genuine leather

Technical data sheet leather Billie

| <u>GENERAL</u>   |   |                               |
|--|---|-------------------------------|
| Thickness  |   | 0.9-1.1                       |
| Average surface  |   | 5,0 sqm                       |
| Finishing  |   | corrected, pigmented, printed |
| Tanning  |   | chrome tanned                 |
| <u>TESTS</u>   | <u>METHOD</u>                           | <u>RESULT / U.M.</u>          |
| Fastness to rubbing - dry 500 cycles                                       | EN ISO 11640 / IUF 450                  | >= 4 grey scale               |
| Fastness to rubbing – wet 250 cycles                                       | EN ISO 11640 / IUF 450                  | >= 4 grey scale               |
| Fastness to rubbing – sweat 80 cycles                                      | EN ISO 11640 / IUF 450                  | >= 4 grey scale               |
| Light fastness   | EN ISO 20105-B02 / IUF 402              | 5 blue scale                  |
| Flexing endurance Ballyflex  | EN ISO 5402 / IUP 20                    | >= 30.000 cycles no damage    |
| Adhesion of finish   | EN ISO 11644 / IUF 470                  | >= 5N/cm                      |
| Tear strength  | EN ISO 3377-1 / IUP 40                  | >= 20N                        |
| Behaviour to fire  | BS5852 source 0+1<br>EN 1021 source 1+2 | pass<br>pass                  |
| <u>CERTIFICATS</u>   |   |                               |
| Ecologically safe production   |   |                               |
| Compliant to requirements of REACH-ILO PCP-DMF-AZO dyestuffs               |   |                               |
|  |   |                               |
| <u>CLEANING INSTRUCTIONS</u>   |   |                               |
| Slightly damp cloth.   |   |                               |
| <u>REMARKS</u>   |   |                               |
| ***INTENSIVE DOMESTIC/CONTRACT USE   |   |                               |
| Slight color differences between production batches can occur.             |   |                               |
| The test results only apply to the samples tested.                         |   |                               |
| Buvetex can't be kept liable for inappropriate use of the genuine leather. |   |                               |