

# Collection Leading

Genuine leather

Technical data sheet leather Leading

<u>GENERAL</u>		
Thickness		1.2-1.4
Average surface		5,0 sqm
Finishing		slightly corrected, semi-aniline
Tanning		chrome tanned
<u>TESTS</u>	<u>METHOD</u>	<u>RESULT / U.M.</u>
Fastness to rubbing - dry 500 cycles	EN ISO 11640 / IUF 450	>= 4 grey scale
Fastness to rubbing – wet 250 cycles	EN ISO 11640 / IUF 450	>= 4 grey scale
Fastness to rubbing – sweat 80 cycles	EN ISO 11640 / IUF 450	>= 4 grey scale
Light fastness	EN ISO 20105-B02 / IUF 402	4/5 blue scale
Flexing endurance Ballyflex	EN ISO 5402 / IUP 20	>= 30.000 cycles no damage
Adhesion of finish	EN ISO 11644 / IUF 470	>= 3,5 N/cm
Tear strength	EN ISO 3377-1 / IUP 40	>= 20N
Behaviour to fire	BS5852 source 0+1 EN 1021 source 1+2	pass pass
<u>CERTIFICATS</u>		
Ecologically safe production		
Compliant to requirements of REACH-ILO PCP-DMF-AZO dyestuffs		
<u>CLEANING INSTRUCTIONS</u>		
Slightly damp cloth.		
<u>REMARKS</u>		
***INTENSIVE DOMESTIC/CONTRACT USE		
Slight color differences between production batches can occur.		
The test results only apply to the samples tested.		
Buvetex can't be kept liable for inappropriate use of the genuine leather.		