

# Collection Oscar

Genuine leather  
Technical data sheet Oscar

<u>GENERAL</u>		
Thickness		1,3-1,5 mm
Average surface		5,0 sqm
Finishing		corrected, pigmented
<u>TESTS</u>	<u>METHOD</u>	<u>RESULT / U.M.</u>
Fastness to rubbing Veslic- dry 500 cycles	UNI EN ISO 11640 / IUF 450	>= 4 grey scale
Fastness to rubbing Veslic- wet 200 cycles	UNI EN ISO 11640 / IUF 450	>= 3-4 grey scale
Fastness to rubbing Veslic- sweat 80 cycles	UNI EN ISO 11640 / IUF 450	>= 3-4 grey scale
Colour fastness to light	UNI EN ISO 20 105 B 02 / IUF 402	>= 3 blue scale
Flexing endurance Bally Flex no damage	UNI EN ISO 5402 / IUP 20	>= 30.000 cycles
Tear strength (Bauman Method)	UNI EN 3377-1 / IUP 40	>= 20 N
Finish adhesion	UNI EN ISO 11644 / IUF 470	>= 2 N/cm
Burning behaviour	BS5852 source 0+1 EN1021 part 1+2	pass pass
<u>CERTIFICATS</u>		
Ecologically safe production.		
Compliant to requirements of REACH, ILO PCP, DMF and AZO dyestuffs		
<u>CLEANING INSTRUCTIONS</u>		
Slightly damp cloth		
<u>REMARKS</u>		
**** INTENSIVE DOMESTIC/CONTRACT USE		
Slight color differences between production batches can occur.		
The test results only apply to the samples tested.		
Buvetex can't be kept liable for inappropriate use of the artificial leather.		