

Collection Scarlet

Artificial leather

Technical data sheet

<u>GENERAL</u>		
Composition surface	100% PVC	
Composition back cloth	100% PES	
Roll width	137cm	
Roll length	30m	
Weight	550 gr/m ²	
Thickness	1.00mm	
<u>TESTS</u>	<u>METHOD</u>	<u>RESULT / U.M.</u>
Fastness to rubbing - dry	UNI EN ISO 11640	5
Fastness to rubbing - wet	UNI EN ISO 11640	4/5
Colour fastness to light	UNI EN ISO 105 B 02	6+
Colour fastness to perspiration	UNI EN ISO 105 E 04	5
Flexing endurance Bally Flex	UNI EN ISO 5401	>100.000
Resistance to blocking	UNI EN ISO BS 3424	no blocking
Martindale abrasion	UNI EN ISO 12947-2	>= 51.200 rubs
Anti-bacterial activity	UNI EN ISO 20743 -8.2	pass
Conformity to REACH	-	pass
Burning behaviour	BS 5852 source 0 + 1 EN 1021-1 / EN 1021-2	pass
<u>CERTIFICATS</u>		
ECE R NO 118 (2005) + Rev 1 (2012) annex 8		
<u>GENERAL INFORMATION</u>		
<u>CLEANING INSTRUCTIONS</u>		
<p>Water and neutral soap.</p> <p>The following disinfectants do not have a negative impact on the coating: sagrotan med, octenisept, isopropylalcohol, dettol (10% solution), sterilium, softasept, jood tinktur, kodan tinktur forte, hanssamed spray, sagrotan spray.</p>		
<u>REMARKS</u>		
**** INTENSIVE DOMESTIC/CONTRACT USE		

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the artificial leather.