

# Collection Tauros

Genuine leather

Technical data sheet

<u>GENERAL</u>		
Thickness		1,3-1,5 mm
Average surface		4,8-5,0 sqm
Finishing		embossed Eur. bovine
<u>TESTS</u>	<u>METHOD</u>	<u>RESULT / U.M.</u>
Fastness to rubbing Veslic- dry	UNI EN ISO 11640	>= 4
Fastness to rubbing Veslic- wet	UNI EN ISO 11640	>= 3/4
Rub fastness Crock test (dry / wet )	UNI EN ISO 105 X 12	-
Colour fastness to light	UNI EN ISO 105 B 02	>= 5
Sweat fastness (alkaline solution)	UNI EN ISO 11640	>= 3/4
Flexing endurance Bally Flex	UNI EN ISO 5402	>50.000 cycles
Tensile strength	UNI EN ISO 3376	-
Elongation at break	UNI EN ISO 3376	-
Tear strength (Bauman Method)	UNI EN 3377-1	>= 20
Finish adhesion	UNI EN ISO 11644	>= 2
Burning behaviour	IMO RES A 652 (16) MED B 8491	pass
<u>CERTIFICATS</u>		
<u>CLEANING INSTRUCTIONS</u>		
<u>REMARKS</u>		
<b>**** INTENSIVE DOMESTIC/CONTRACT USE</b>		
Slight color differences between production batches can occur.		
The test results only apply to the samples tested.		
Buvetex can't be kept liable for inappropriate use of the artificial leather.		