


# Corone

## Collection Ambiance

### Technical data sheet

<b>GENERAL</b>		
Composition		47% VIS + 51% PES + 2% CO textured
Roll width		138 cm
Roll length		
Weight		1174 gr/m
<b>TESTS</b>	<b>METHOD</b>	<b>RESULT / U.M.</b>
Martindale abrasion	UNI EN ISO 12947-2	>40.000 cycles
Pilling	UNI EN ISO 12945-2	4-5
Colourfastness to light	UNI EN ISO 105 B02	6
Fastness to rubbing (dry+wet)	UNI EN ISO 105 X12	5
Breaking strength	UNI EN ISO 13934-1 (N)	2200 warp / 1100 weft
Seam slippage	UNI EN ISO 13936-2	2 warp + 3 weft
Tear strength	UNI EN ISO 13937-3	200 warp / 300 weft
Burning behaviour	UNI EN ISO FR 1021 part 1	pass
<b>CERTIFICATS</b>		
 <p>FR EN 1021 PART 2 OPTIONAL</p>		
<b>CLEANING INSTRUCTIONS</b>		
