








# Loom

## Collection Ambiance

### Technical data sheet

<b>GENERAL</b>		
Composition	100% PES	
Roll width	138-140 cm	
Roll length	50 m	
Weight	689 gr/m	
<b>TESTS</b>	<b>METHOD</b>	<b>RESULT / U.M.</b>
Martindale abrasion	UNI EN ISO 12947-2	>45.000 cycles
Pilling	UNI EN ISO 12945-2	5
Colourfastness to light	UNI EN ISO 105 B02	7
Fastness to rubbing (dry+wet)	UNI EN ISO 105 X12	4-5
Breaking strength	UNI EN ISO 13934-1 (N)	1578 warp / 2404 weft
Seam slippage	UNI EN ISO 13936-2	2.0 warp + 3.7 weft
Tear strength	UNI EN ISO 13937-3	153 warp + 326 weft
Burning behaviour	UNI EN ISO FR 1021 part 1	pass
<b>CERTIFICATS</b>		
 <p>FR EN 1021 PART 2 OPTIONAL</p>		
<b>CLEANING INSTRUCTIONS</b>		
 <p>EASY CLEAN</p>     		



Dijle 17/A  
2800 Mechelen  
TEL : 0032-15/40.90.60  
[www.buvetex.be](http://www.buvetex.be)

