



Moins

Collection Ambiance

Technical data sheet

GENERAL		
Composition	55% PES + 45% VIS textured	
Roll width	138-140 cm	
Roll length	50 m	
Weight	689 gr/m	
TESTS	METHOD	RESULT / U.M.
Martindale abrasion	UNI EN ISO 12947-2	>30.000 cycles
Pilling	UNI EN ISO 12945-2	5
Colourfastness to light	UNI EN ISO 105 B02	5
Fastness to rubbing (dry+wet)	UNI EN ISO 105 X12	5
Breaking strength	UNI EN ISO 13934-1 (N)	2303 warp / 1414 weft
Seam slippage	UNI EN ISO 13936-2	2.0 warp + 2.0 weft
Tear strength	UNI EN ISO 13937-3	118 warp + 306 weft
Burning behaviour	UNI EN ISO FR 1021 part 1	pass
CERTIFICATS		
 FR EN 1021 PART 2 OPTIONAL		
CLEANING INSTRUCTIONS		
		



Dijle 17/A
2800 Mechelen
TEL : 0032-15/40.90.60
www.buvetex.be

