


Oscar

Genuine leather collection

Technical data sheet

GENERAL		
Thickness		1,3-1,5mm
Average surface		3,6sqm
Finishing		aniline, paraffin & oil finish
Tanning		chrome tanned
TESTS	METHOD	RESULT / U.M.
Fastness to rubbing Veslic – dry (50 cycles)	UNI EN ISO 11640 / IUF 450	>= 3
Fastness to rubbing Veslic – wet (20 cycles)	UNI EN ISO 11640 / IUF 450	>= 2-3
Fastness to rubbing Veslic – sweat (20 cycles)	UNI EN ISO 11640 / IUF 450	>= 2-3
Colour fastness to light	UNI EN ISO 105 B02	>= 3
Flexing endurance Bally Flex	UNI EN ISO 5402	>= 20.000 cycles
Tear strength (Bauman method)	UNI EN 3377-1	>= 20 N
Finish adhesion	UNI EN ISO 11644	n/a
Burning behaviour	UNI EN ISO 1021 1+2	pass
CERTIFICATS		
Ecologically safe production		
Compliant to the requirements of REACH, ILO, PCP, DMF and AZO dyestuffs		
 FIRE RETARDANT		
CLEANING INSTRUCTIONS		
Slightly damp cloth		



Dijle 17/A
2800 Mechelen
TEL : 0032-15/40.90.60
www.buvetex.be

REMARKS

*****INTENSIVE DOMESTIC AND CONTRACT USE*****

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the genuine leather.