



Ruban

Collection Ambiance

Technical data sheet

GENERAL		
Composition		96% PES + 4% RCO textured
Roll width		140 cm
Roll length		50 m
Weight		867 gr/m
TESTS	METHOD	RESULT / U.M.
Martindale abrasion	UNI EN ISO 12947-2	>100.000 cycles
Pilling	UNI EN ISO 12945-2	3-4
Colourfastness to light	UNI EN ISO 105 B02	5
Fastness to rubbing (dry+wet)	UNI EN ISO 105 X12	3-4
Breaking strength	UNI EN ISO 13934-1 (N)	>350
Seam slippage	UNI EN ISO 13936-2	2.6 warp + 4 weft
Tear strength	UNI EN ISO 13937-3	>20
Burning behaviour	UNI EN ISO FR 1021 part 1	pass
CERTIFICATS		
 <p>FR EN 1021 PART 2 OPTIONAL</p>		
CLEANING INSTRUCTIONS		
 <p>EASY CLEAN</p>		
