


# Hit

## Collection Crypton

### Technical data sheet

<b>GENERAL</b>		
Composition		100%PL
Roll width		137cm
Roll length		30m
Weight		670gr/m
<b>TESTS</b>	<b>METHOD</b>	<b>RESULT / U.M.</b>
Martindale abrasion	UNI EN ISO 12947-2	>50.000 cycles
Pilling (5000 cycles)	UNI EN ISO 12945-2	4- 5
Colourfastness to light	UNI EN ISO 105 B02	4
Fastness to rubbing (wet)	UNI EN ISO 105 X12	4-5
Fastness to rubbing (dry)	UNI EN ISO 105 X12	3-4
Breaking strength	UNI EN ISO 13934-1 (N)	880 weft / 650 warp
Breaking elongation	UNI EN ISO 13934-1 (%)	22.5 weft / 33.8 Warp
Bacteria resistance + fungal growth resistance	EN ISO 20743 AATCC4352+30+6275	95% (+/- 5%)
Hydrostatic resistance	AATCC 127 (moisture barrier)	>100 cm
burning behaviour	FR BS5852 source 0+1	pass
<b>CERTIFICATS</b>		
<p>REACH compliant, moisture resistant, liquid &amp; oil repellent, odor resistant, anti-microbial, fungal growth resistant, ecofriendly (Greenguard Gold Certified)</p>  <p>FIRE RETARDANT</p>		

**CLEANING INSTRUCTIONS**



STAIN RESISTANT, with water and mild detergent (1% dishwashing liquid -laundry detergent)



**REMARKS**

\*\*\*INTENSIVE DOMESTIC AND CONTRACT USE\*\*\*

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the fabric.