


Sarda

Genuine leather collection

Technical data sheet

GENERAL		
Thickness		0,8-1,0mm
Average surface		4,8-5,0sqm
Finishing		embossed Eur. bovine
Tanning		chrome tanned
TESTS	METHOD	RESULT / U.M.
Fastness to rubbing Veslic - dry	UNI EN ISO 11640	>= 4
Fastness to rubbing Veslic - wet	UNI EN ISO 11640	>= 3/4
Colour fastness to light	UNI EN ISO 105 B02	>= 5
Sweat fastness (alkaline solution)	UNI EN ISO 11640	>=3/4
Flexing endurance Bally Flex	UNI EN ISO 5402	>50.000
Tear strength (Bauman method)	UNI EN 3377-1	>=20 N
Finish adhesion	UNI EN ISO 11644	>=2 N/cm
Burning behaviour	IMO RES A652 (16) - MED B8491	pass
CERTIFICATS		
 <p>FIRE RETARDANT</p>		
CLEANING INSTRUCTIONS		
Slightly damp cloth.		
REMARKS		
<p>INTENSIVE USE FOR CONTRACT, DOMESTIC AND INDUSTRY</p> <p>Slight color differences between production batches can occur.</p> <p>The test results only apply to the samples tested.</p> <p>Buvetex can't be kept liable for inappropriate use of the genuine leather.</p>		